

## Method for making non-clinker cement by wet-milling flyash and product thereof

**Patent number:** CN1105344  
**Publication date:** 1995-07-19  
**Inventor:** JIESHENG GAO (CN); QINGLIN DU (CN)  
**Applicant:** LIANYUNGANG CITY INST OF BUILD (CN)  
**Classification:**  
- **international:** **C04B7/52; C04B7/00;** (IPC1-7): C04B7/28; C04B18/06; C04B28/18  
- **european:** C04B7/52  
**Application number:** CN19940111221 19940113  
**Priority number(s):** CN19940111221 19940113

**Report a data error here**

### Abstract of **CN1105344**

The non-clinker cement is made up from wet flyash discharged from steam-power plant, lime and gypsum through separately grinding and mixing. This low-grade (No.275) cement may be used to produce non-burning brick or building block, mortar and concrete No.13, or to mix with ordinary Port/and cement.

---

Data supplied from the **esp@cenet** database - Worldwide